

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35.U.S.C. 371

EXPRESS MAIL LABEL No
EJ339573303US

DATE
16 JUNE 2000

ATTORNEY'S DOCKET NO
A33291 PCT USA

U.S. APPLICATION NO

09/581804

INTERNATIONAL APPLICATION NO
PCT/KR99/00101

INTERNATIONAL FILING DATE
04 MARCH 1999

PRIORITY DATE CLAIMED
29 OCTOBER 1998

TITLE OF INVENTION

THERMOPLASTIC TRANSPARENT RESIN COMPOSITION AND METHOD OF MANUFACTURING SAME

APPLICANT(S) FOR DO/EO/US

Koon-Hoon Yoo, Yang-Hyun Shin and Chan-Hong Lee

Applicant herewith submits to the United States Designated /Elected Office (DO/EO/US) the following items and other information:


1. ☒ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(I).
4. ☐ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☐ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
- ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
- ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
- ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☐ A FIRST preliminary amendment.
14. ☐ A SECOND or SUBSEQUENT preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☒ Other items or information:

A copy of International Publication as published (including 18 pages spec and 3 pages claims)
International Search Report
PCT/ISA/220
PCT/RO/101
PCT/IB/304

09/581804

INTERNATIONAL APPLICATION NO PCT/KR99/00101		INTERNATIONAL FILING DATE 04 MARCH 1999		PRIORITY DATE CLAIMED 29 OCTOBER 198	
17. [X] The following fees are submitted:				<div style="border: 1px solid black; padding: 2px; display: inline-block;"> 534 Rec'd PCT/PTC CALCULATIONS </div> <div style="display: inline-block; vertical-align: middle;"> 16 JUN 2000 </div>	
Basic National Fee (37 CFR 1.492(a)(1)-(5): Neither international preliminary examination fee (37 CFR 1.482) Nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO (1.492(a)(3)) \$970.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO (1.492(a)(5)) \$840.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO (1.492(a)(2)) \$690.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) (1.492(a)(1)) \$670.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) \$ 96.00 <div style="text-align: right;">ENTER APPROPRIATE BASIC FEE AMOUNT = \$ 840.00</div>					
Surcharge of \$130.00 for furnishing the oath or declaration later than [] 20 [] 30 months from the earliest claimed priority date (37 C.F.R. 1.492(e)).				\$	
Claims	Number Filed	Number Extra	Rate	\$	
Total Claims	12 -20=		X \$ 18.00	\$	
Independent Claims	2 -3=		X \$ 78.00	\$	
Multiple dependent claim(s) (if applicable)			+ \$260.00	\$	
TOTAL OF ABOVE CALCULATIONS				= \$ 840.00	
Reduction by ½ for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28).				\$	
SUBTOTAL				= \$ 840.00	
Processing fee of \$130.00 for furnishing the English translation later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				+ \$	
TOTAL NATIONAL FEE				= \$ 840.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				+ \$ 40.00	
TOTAL FEES ENCLOSED				= \$ 880.00	
				Amt. refunded	\$
				charged	\$
a. [X] A check in the amount of \$ <u>840 & 40</u> to cover the above fees is enclosed. b. [] Please charge our Deposit Account No. <u>02-4377</u> in amount of \$ <u> </u> to cover the above fees. A copy of this sheet is enclosed. c. [X] The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>02-4377</u> . A copy of this sheet is enclosed.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO:					
BAKER BOTTS L.L.P. 30 Rockefeller Plaza New York, New York 10112-4498				 Signature Paul D. Ackerman June 16, 2000 Date 39,891 Registration No.	

534 Rec'd PCT/PTC 16 JUN 2000

**THERMOPLASTIC TRANSPARENT RESIN COMPOSITION AND METHOD OF
MANUFACTURING SAME****BACKGROUND OF THE INVENTION****(a) Field of the Invention**

5 The present invention relates to a thermoplastic transparent resin
composition, and more particularly, to a thermoplastic transparent resin
composition which is resistant to shocks, chemically resistant, easily processed,
and highly transparent. The present invention also relates to a method for
manufacturing the thermoplastic transparent resin composition in which, when
10 performing graft copolymerization of a methacrylic acid or an acrylic alkylester
compound, an aromatic vinyl compound, and a vinylcyan compound in a mixture
of a small aperture polybutadiene rubber latex and a large aperture
polybutadiene rubber latex, both having a suitable gel content, a refraction
coefficient is maximized by controlling the mixture ratio of these monomers,
15 thereby realizing the advantages of the resin composition stated above.

(b) Description of the Related Art

Many various products today use transparent plastic parts for both
practical reasons and to provide distinguishable characteristics to a product.
Examples include the plastic screen cover on a cell phone, a washing machine
20 cover that enables the user to view the contents being washed, portions of the
housing of a PC monitor, pager housings, the housings and covers of home
appliances, etc. However, the typically used ABS (acrylonitrile-butadiene-
styrene) copolymer resin, although providing good shock resistance, chemical

resistance, processability, and surface gloss, has limited transparency.

The following are some of the methods for providing transparency in plastic materials:

- 1) A method using transparent polycarbonate resin.
- 5 2) A method of providing shock resistance to transparent PMMA (polymethylmethacrylate) resin (U.S. Patent No. 3,787,522, Japanese Patent No. Sho 63-42940).
- 3) A method of providing transparency to HIPS (high impact polystyrene) resin (European Patent No. 0,703,252).

10 However, in the method of using polycarbonate resin, although this material has good transparency and shock resistance at room temperature, it is not highly resistant to chemicals and does not display high resistance to shocks at low temperatures. This material also has problems related to processability, making it difficult to manufacture this product to large sizes. With regard to
15 PMMA resin, though providing good transparency and processability, this material has an extremely low level of resistance against shocks. Finally, regarding HIPS resin, this material has a low level of resistance against chemicals and is easily scratched.

 U.S. Patent No. 4,767,833, in an effort to solve the above problems,
20 discloses a transparent resin in which monomers such as methylmethacrylate, styrene and acrylonitrile are graft copolymerized in SBR (styrene-butadiene rubber) latex such that properties of shock resistance, chemical resistance, and processability are realized. However, this resin is limited in its resistance to

shocks at low temperatures and displays a limited degree of transparency.

SUMMARY OF THE INVENTION

The present invention has been made in an effort to solve the above
5 problems.

It is an object of the present invention to provide a thermoplastic transparent resin composition and a method of manufacturing the same in which the resin composition displays high resistance to shocks at both room temperature and low temperatures, high chemical resistance, good
10 processability, high surface gloss, and excellent transparency.

To achieve the above object the present invention provides a thermoplastic transparent resin composition comprising 3-15 parts by weight of small aperture polybutadiene rubber latex, 5-25 parts by weight of large aperture polybutadiene rubber latex, 40-70 parts by weight of a methacrylic acid
15 alkylester compound or an acrylic acid alkylester compound, 15-30 parts by weight of an aromatic vinyl compound, and 1-20 parts by weight of a vinylcian compound.

Further, the present invention provides a method of manufacturing a thermoplastic transparent resin composition including the steps of a) producing a
20 small aperture polybutadiene rubber latex having an average particle diameter of 600-1500 \AA , a gel content of 70-95%, and a swelling index of 12-30 by reacting butadiene at 55-70°C using a polymerization initiator, b) producing a large

aperture polybutadiene rubber latex having a particle diameter of 2600-5000 Å, a gel content of 70-95%, and a swelling index of 12-30 by enlarging the small aperture polybutadiene rubber latex particles, and c) performing graft copolymerization at 65-80°C by continuously or separately adding 3-15 parts by weight of the small aperture polybutadiene rubber latex of step a), 5-25 parts by weight of the large aperture polybutadiene rubber latex of step b), 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound, 15-30 parts by weight of an aromatic vinyl compound, and 1-20 parts by weight of a vinylcian compound.

10

DETAILED DESCRIPTION OF THE PRESENT INVENTION

In the present invention, when producing an ABS resin comprised of acrylonitrile having high chemical resistance, butadiene having good resistance to shocks, and styrene providing good processability, methylmethacrylate is introduced, and by controlling a content and mixture ratio of each component, a refraction coefficient of polybutadiene rubber latex and a refraction coefficient of a mixture of the methymethacrylate, styrene, and acrylonitrile, grafted in the rubber latex, are maximized. Accordingly, a thermoplastic transparent resin is manufactured having high levels of shock resistance, chemical resistance, and processability, in addition to excellent transparency.

The thermoplastic transparent resin composition of the present invention is manufactured by graft copolymerizing, using an emulsion polymerization method, a mixture of a small aperture polybutadiene rubber having a particle

diameter of 600-1500 Å, a gel content of 70-95%, and a swelling index of 12-30 and a large aperture polybutadiene rubber latex having a particle diameter of 2600-5000 Å, a gel content of 70-95%, and a swelling index of 12-30, and monomers grafted in the mixture of a methacrylic acid or an acrylic acid alkylester compound, an aromatic vinyl compound, and a vinylcian compound.

The particle diameter and gel content of the polybutadiene rubber latex used in the present invention greatly influence properties of the inventive resin composition such as transparency and resistance to shocks. Therefore, particle diameter size and gel content must be suitably controlled to ensure that optimal levels of such properties are realized. That is, in the case of the rubber latex particle size, although transparency is increased with decreases in particle size, shock resistance and fluidity are decreased, whereas the opposite results with increases in particle size. Further, if the gel content of the rubber latex is low, since the monomers undergo significant swelling in the rubber latex during graft reaction, an external particle diameter of the rubber latex is increased. This limits transparency but improves resistance to shocks. Here also, the opposite effect results with increases in the gel content.

Further, a refractive coefficient of the monomer mixture is directly related to transparency of the inventive resin composition. The refractive coefficient is controlled by a mixture ratio of the monomers. That is, since a refractive coefficient of polybutadiene is approximately 1.518, the remaining grafted components must be similar to this level to realize a high level transparency. Refractive coefficients for each component are 1.49 for the methylmethacrylate,

1.59 for the styrene, and 1.518 for the acrylonitrile.

During the graft copolymerization reaction, each component can be added all at once, or each separately (or partially for each component) in a continuous manner. The present invention performs the adding of components using both these methods. This will be described in more detail hereinafter.

A method of manufacturing the thermoplastic transparent resin composition of the present invention will now be described.

1) Manufacture of polybutadiene rubber latex

a) Manufacture of small aperture rubber latex

100 parts by weight of 1,3-butadiene, 1-4 parts by weight of a emulsifying agent, 0.1-0.6 parts by weight of a polymerization initiator, 0.1-1.0 parts by weight of an electrolyte, 0.1-0.5 parts by weight of a molecular weight controlling agent, and 90-130 parts by weight of ion exchange water are added all at once, and reacted at 50-65°C for 7-12 hours. Next, 0.5-1.2 parts by weight of a molecular weight controlling agent is further added and reacted at 55-70°C for 5-15 hours, thereby producing small aperture polybutadiene rubber latex having an average particle diameter of 600-1500 Å, a gel content of 70-95%, and a swelling index of 12-30.

As the emulsifying agent, it is possible to use one or a mixture of two or more of the following: alkyl aryl sulfonate, alkali methyl alkyl sulfate, sulfonated alkylester, fatty acid soap, and rosin acid alkali salt. As the polymerization initiator, it is possible to use a water soluble persulfate or peroxy compound, or an oxidation-reduction compound. The most suitable water soluble persulfates

are sodium and potassium. For a fat soluble polymerization initiator, it is possible to use cumene peroxide, diisopropyl benzene hydroperoxide, azobisisobutyronitrile, tertiary butyl hydroperoxide, paramethane hydroperoxide, and benzoyl peroxide. For the electrolyte, it is possible use one or a mixture of
5 two or more of the following: KCl, NaCl, KHCO_3 , NaHCO_3 , K_2CO_3 , Na_2CO_3 , KHSO_3 , NaHSO_3 , $\text{K}_4\text{P}_2\text{O}_7$, K_3PO_4 , Na_3PO_4 , K_2HPO_4 , and Na_2HPO_4 .

An important factor in determining gel content and the swelling index of the rubber latex is polymerization temperature. The type of initiator used also influences these two characteristics of the rubber latex.

10 b) Manufacture of large aperture rubber latex (small aperture rubber latex adhesion process)

3.0-4.0 parts by weight of an acetic acid aqueous solution is slowly added over a period of one hour to 100 parts by weight of the small aperture rubber latex having a particle diameter of $600-1500 \text{ \AA}$, a gel content of 70-95%,
15 and a swelling index of 12-30, thereby enlarging the particle size. Stirring is then discontinued and a large aperture rubber latex results, the large aperture rubber latex having a particle diameter of $2600-5000 \text{ \AA}$, a gel content of 70-95%, and a swelling index of 12-30.

To provide shock resistance to the rubber latex, although it is possible to
20 manufacture the large aperture rubber latex using a direct polymerization method (Japanese Laid-Open Patent No. 56-136807), a long reaction time is required and the gel content level that can be obtained is limited with this method. Accordingly, in order to produce a large aperture rubber latex in a short

amount of time while maintaining a high gel content, it is preferable, as described above, to first manufacture a small aperture rubber latex having a high gel content, then add an acidic material to the rubber latex to enlarge the particles, thereby producing a large aperture rubber latex.

5 2) Manufacture of graft copolymerization material

Graft copolymerized in a mixture of 3-15 parts by weight of the small aperture polybutadiene rubber latex and 5-25 parts by weight of the large aperture polybutadiene rubber latex are 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound, 15-30 parts by weight of an aromatic vinyl compound, 1-20 parts by weight of a vinylcian
10 compound, 0.2-0.6 parts by weight of an emulsifying agent, 0.2-0.6 parts by weight of a molecular weight controlling agent, and 0.05 to 0.3 parts by weight of a polymerization initiator.

In the above, a suitable polymerization temperature is 65-80°C, and a
15 suitable polymerization time is 4-7 hours. In the polymerization reaction, it is possible to use methymethacrylate for the methacrylic acid alkylester compound or acrylic acid alkylester compound; for the aromatic vinyl compound, it is possible to use styrene, α -methylstyrene, o-ethylstyrene, p-ethylstyrene, or vinyl toluene; and for the vinylcian compound, it is possible to use acrylonitrile,
20 methacrylonitrile, or ethacrylonitrile.

As the emulsifying agent used in the polymerization reaction, it is possible to use one or a mixture of two or more of alkyl aryl sulfonate, alkali methyl alkyl sulfate, sulfonated alkylester, fatty acid soap, and rosin acid alkali

salt. For the molecular weight controlling agent, tertiary dodecyl mercaptan is generally used. As the polymerization initiator, it is possible to use an oxidation-reduction catalyst realized through a mixture of (a) a peroxide such as cumene peroxide, diisopropyl benzene hydroperoxide, and persulfuric acid salt, and (b) a
5 reducing agent such as sodium formaldehyde sulfoxylate, sodium ethylenediaminetetraacetic, primary iron sulfate, dextrose, pyrroline acid sodium, and sulfurous sodium.

After polymerization is complete, a polymerization conversion rate of the obtained latex is over 98%. An oxidation preventing agent and a stabilizer is
10 then added to the latex, and at a temperature over 80°C, the latex is coagulated using a calcium chloride aqueous solution, after which the latex is desiccated and dried, thereby obtaining a powder.

Stability of the graft copolymerized latex manufactured in the above is determined by measuring a solidification rate (%) using Equation 1 below.

15 [Equation 1]

Solidification(%) = produced solidification wt.(g) in reactor/ weight of all rubber and monomers X 100

A solidification rate of over 0.7% is indicative of an extremely low latex stability, and there will occur difficulty in realizing suitable graft copolymerization
20 as a result of the large presence of solid material.

After adding the oxidation preventing agent and stabilizer, pellets are manufactured from the powder using a biaxial extruding mixer at a temperature between 200 and 230°C. The pellets are again extracted to measure properties

of the same.

Since the mixture of the monomers in the present invention changes the refraction coefficient in the resulting inventive resin, it is important to obtain a suitable monomer mixture to realize good transparency. That is, since a refractive coefficient of polybutadiene is approximately 1.518, an entire refractive coefficient of the grafted compound must be 1.510-1.526, preferably between 1.513 and 1.521. A refractive coefficient not reaching 1.510 or exceeding 1.527 is not suitable in the present invention.

The present invention is further explained in more detail with reference to the following examples. The invention can be utilized in various ways and is not intended to be confined to the examples.

[Example 1]

I. Manufacture of polybutadiene rubber latex

A) Manufacture of small aperture rubber latex

Added all at once to a nitrogen substituted polymerization autoclave were 110 parts by weight of ion exchange water; 100 parts by weight of 1,3-butadiene as a monomer; 1.2 parts by weight of rosin acid potassium salt as a emulsifying agent; 1.5 parts by weight of oleic acid potassium salt; 0.1 parts by weight of sodium carbonate (Na_2CO_3) as electrolyte; 0.5 parts by weight of potassium hydrogen carbonate (KHCO_3); and 0.3 parts by weight of tertiary dodecyl mercaptan (TDDM) as a molecular weight controlling agent. Next, a reaction temperature was increased to 55°C , and after adding 0.3 parts by weight of persulfuric acid potassium as an initiator to begin the reaction, reaction

was performed for 10 hours. Following this step, 0.05 parts by weight of tertiary dodecyl mercaptan were again added to the mixture, after the same was reacted for 8 hours at 65°C. A rubber latex obtained using this method was analyzed using a method described below.

5 (1) Gel content and swelling index

After solidifying the rubber latex using diluted acid or metal salt, the rubber latex is washed then dried for 24 hours in a vacuum oven set at 60°C. Subsequently, the obtained rubber lumps are cut in small (approximately 1g) pieces using scissors, and the pieces are put into 100g of toluene then stored in
10 a darkroom at room temperature for 48 hours. After storage, the material is separated into sol and gel, and a gel content and swelling index are measured using Equation 2 and Equation 3 below, respectively.

[Equation 2]

Gel content(%) = weight of insoluble portion (gel) / weight of sample X
15 100

[Equation 3]

Swelling index = weight of swelled gel / weight of gel

(2) Particle diameter

Particle diameter is measured by a dynamic laser light scattering method
20 using a Nicomp 370 HPL.

Using the above methods, the gel content of the particle diameter was 90%, the swelling index was 18, and the particle diameter was 1000 Å.

B) Manufacture of large aperture rubber latex (small aperture rubber

latex adhesion process)

Added to a reactor were 100 parts by weight of the small aperture rubber latex manufactured above. Next, at a stirring speed of 10 rpm and a temperature of 30°C, 3.5 parts by weight of an acetic acid aqueous solution were slowly
5 added to the small aperture rubber latex over a period of one hour, after which stirring was discontinued and the mixture was left to stand for 30 minutes, thereby completing the manufacture of the large aperture rubber latex. The large aperture rubber latex obtained through an adhesion method in this manner had a particle diameter of 3000 Å, a gel content of 90%, and a swelling index of 17.

10 II. Manufacture of graft copolymerization material

Added all at once at a temperature of 50°C to a mixture of 8 parts by weight of the small aperture rubber latex and 10 parts by weight of the large aperture rubber latex were the components of Example 1 shown in Tables 1 and 2, i.e. 90 parts by weight of ion exchange water, 0.2 parts by weight of an oleic
15 acid sodium emulsifying agent, 11.98 parts by weight of methylmethacrylate, 4.52 parts by weight of styrene, 4 parts by weight of acrylonitrile, 0.2 parts by weight of tertiary dodecyl mercaptan, 0.048 parts by weight of pyrophosphoric acid sodium, 0.012 parts by weight of dextrose, 0.001 parts by weight of primary iron sulfate, and 0.04 parts by weight of cumene hydroperoxide. The mixture
20 was reacted while slowly increasing the temperature to 73°C over a period of 2 hours.

Next, continuously added to the above mixture over a period of 4 hours was an emulsifying agent mixture of 70 parts by weight of ion exchange water,

13

0.4 parts by weight of an oleic acid sodium emulsifying agent, 35.92 parts by weight of methylmethacrylate, 13.58 parts by weight of styrene, 12 parts by weight of acrylonitrile, 0.25 parts by weight of tertiary dodecyl mercaptan, 0.048 parts by weight of pyrophosphoric acid sodium, 0.012 parts by weight of dextrose, 0.001 parts by weight of primary iron sulfate, and 0.10 parts by weight of cumene hydroperoxide. The temperature was again increased to 76°C over a period of one hour to mature the mixture, thereby completing the reaction.

A polymerization conversion rate of the obtained latex was 99.8% and a solidification rate of the same was 0.12%. A powder was obtained by solidifying the latex using a calcium chloride aqueous solution then washing the same.

[Example 2]

The same method as in Example 1 was used to manufacture small and large aperture rubber latex, and graft copolymerization material, but a composition ratio for Example 2 shown in Tables 1 and 2 was used instead of that for Example 1.

[Comparative Examples 1-5]

The same method as in Example 1 was used to manufacture small and large aperture rubber latex, and graft copolymerization material, but a composition ratio for Comparative Examples 1-5 shown in Tables 1 and 2 was used instead of that for Example 1.

[Comparative Example 6]

The same method as in Example 1 was used to manufacture small aperture rubber latex and graft copolymerization material, but a composition ratio

for Comparative Example 6 shown in Tables 1 and 2 was used instead of that for Example 1. Large aperture rubber latex in Comparative Example 6 was manufactured as described below.

Manufacture of large aperture rubber latex (direct polymerization
5 method)

Added all at once to a nitrogen substituted polymerization autoclave were 83 parts by weight of ion exchange water; 100 parts by weight of 1,3-butadiene; 1.2 parts by weight of rosin acid potassium salt as an emulsifying agent; 1.5 parts by weight of oleic acid potassium salt; 0.7 parts by weight of
10 sodium carbonate (Na_2CO_3) as electrolyte; 0.8 parts by weight of potassium hydrogen carbonate (KHCO_3); and 0.3 parts by weight of tertiary dodecyl mercaptan (TDDM) as a molecular weight controlling agent. Next, a reaction temperature was increased to 65°C , and after adding 0.3 parts by weight of persulfuric acid potassium as an initiator to initiate the reaction, reaction was
15 performed for 45 hours while the temperature was raised to 85°C . A rubber latex obtained using this method was then analyzed, the results of which were a rubber latex having a particle diameter of 3000Å , a gel content of 65%, and a swelling index of 31.

[Applied Example 1]

20 Added to 100 parts by weight of the graft copolymerization material of Example 1 were 0.1 parts by weight of an activator and 0.2 parts by weight of an oxidation preventing material. Next, using a biaxial extruding mixer, pellets were made from the graft copolymerization material and added components in a

cylinder oven set at 210°C. The pellets were extracted to make samples, and properties of the samples were measured, results of which are shown in Table 3.

[Applied Examples 2-8]

The same method as that used in Applied Example 1 was used, but instead of adding the materials to the graft copolymerization material of Example 1, the powder manufactured according to Example 2 and Comparative Examples 1-6 was used for Applied Examples 2-8, respectively. Results of analysis are shown in Table 3.

10 Table 1

1st Reaction	Example 1	Example 2	Comp. Example 1	Comp. Example 2	Comp. Example 3	Comp. Example 4	Comp. Example 5	Comp. Example 6
Ion Exch. Water	90	100	99	91	96	92	90	95
Small Apert. Rubber Latex	8	3	1	4	6	14	---	4
Large Apert. Rubber Latex	10	9	9	8	10	---	14	10 (direct method)
Oleic Acid Sodium	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Methylm ethacryla te	11.98	---	---	15.8	---	---	14.38	19.2
Styrene	4.52	---	---	3.7	---	---	5.63	7.47
Acrylonitr ile	4	---	---	2.5	---	---	2.5	2

Table 2[illegible]

n								
Pyrophosphoric acid sodium	0.048	0.048	0.048	0.048	0.048	0.048	0.048	0.048
Dextrose	0.012	0.012	0.012	0.012	0.012	0.012	0.012	0.012
Primary iron sulfate	0.001	0.001	0.001	0.001	0.001	0.001	0.001	0.001
Cumene hydroperoxide	0.1	0.11	0.1	0.1	0.1	0.1	0.1	0.1
Add. Method	Continuous	continuous	continuous	continuous	continuous	continuous	continuous	continuous
Reaction Time	4 hours	6 hours	6 hours	4 hours	6 hours	6 hours	4 hours	4 hours
Polymer. Conv. Rate(%)	99.8	99.0	99.7	99.7	99.5	99.5	99.3	99.8
Solidification (%)	0.12	0.10	0.10	0.10	0.15	0.10	0.10	0.10

Table 3

	Applied Ex. 1	Applied Ex. 2	Applied Ex. 3	Applied Ex. 4	Applied Ex. 5	Applied Ex. 6	Applied Ex. 7	Applied Ex. 8
Graft copolymerization material	Example 1	Example 2	Comp. Example 1	Comp. Example 2	Comp. Example 3	Comp. Example 4	Comp. Example 5	Comp. Example 6
Notch Isod Shock Strength ASTM D-256	16	11	7	10	14	3	13	13
Fluidity Index ASTM D-1238	14	22	25	22	16	16	18	19

Haze value ASTM D- 1003	3.5	3	3.9	20	24	2.4	8.8	11.2
Chemical Resist. (ethanol solution) (after 14- day storage)	Extremel y High	High	Low	High	High	High	High	High

Although preferred examples of the present invention have been described in detail hereinabove, it should be clearly understood that many variations and/or modifications of the basic inventive concepts herein taught
 5 which may appear to those skilled in the present art will still fall within the spirit and scope of the present invention, as defined in the appended claims.

WHAT IS CLAIMED IS:

1. A thermoplastic transparent resin composition comprising:
 - 3-15 parts by weight of small aperture polybutadiene rubber latex;
 - 5-25 parts by weight of large aperture polybutadiene rubber latex;
 - 5 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound;
 - 15-30 parts by weight of an aromatic vinyl compound; and
 - 1-20 parts by weight of a vinylcian compound.
2. The resin composition of claim 1 wherein the composition further
10 comprises 0.2-0.6 parts by weight of an emulsifying agent, 0.2-0.6 parts by weight of a molecular weight controlling agent, and 0.05-0.3 parts by weight of a polymerization starter.
3. The resin composition of claim 1 wherein the small aperture polybutadiene rubber latex has a particle diameter of 600-1500 \AA , a gel content
15 of 70-95%, and a swelling index of 12-30.
4. The resin composition of claim 1 wherein the large aperture polybutadiene rubber latex has a particle diameter of 2600-5000 \AA , a gel content of 70-95%, and a swelling index of 12-30,
5. The resin composition of claim 1 wherein the methacrylic acid
20 alkylester compound and the acrylic acid alkylester compound are methylmethacrylate.
6. The resin composition of claim 1 wherein the aromatic vinyl compound is selected from the group consisting of styrene, α -methylstyrene, o-

ethylstyrene, p-ethylstyrene, and vinyl toluene.

7. The resin composition of claim 1 wherein the vinylcian compound is selected from the group consisting of acrylonitrile, methacrylonitrile, and ethacrylonitrile.

5 8. A method of manufacturing a thermoplastic transparent resin composition comprising the steps of:

a) producing a small aperture polybutadiene rubber latex having an average particle diameter of 600-1500 Å, a gel content of 70-95%, and a swelling index of 12-30 by reacting butadiene at 55-70°C using a polymerization
10 initiator;

b) producing a large aperture polybutadiene rubber latex having a particle diameter of 2600-5000 Å, a gel content of 70-95%, and a swelling index of 12-30 by enlarging the small aperture polybutadiene rubber latex particles; and

15 c) performing graft copolymerization at 65-80°C by continuously or separately adding 3-15 parts by weight of the small aperture polybutadiene rubber latex of step a), 5-25 parts by weight of the large aperture polybutadiene rubber latex of step b), 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound, 15-30 parts by weight of an
20 aromatic vinyl compound, and 1-20 parts by weight of a vinylcian compound.

9. The method of claim 8 wherein the methacrylic acid alkylester compound and the acrylic acid alkylester compound are methylmethacrylate.

10. The method of claim 8 wherein the aromatic vinyl compound is

21

selected from the group consisting of styrene, α -methylstyrene, o-ethylstyrene, p-ethylstyrene, and vinyl toluene.

11. The method of claim 8 wherein the vinylcian compound is selected from the group consisting of acrylonitrile, methacrylonitrile, and ethacrylonitrile.

5 12. The method of claim 8 wherein in step c), a total refraction coefficient of the compound, excluding the polybutadiene rubber latex, is between 1.510 and 1.526.

[illegible]

**COMBINED DECLARATION
AND POWER OF ATTORNEY**

(Original, Design, National Stage of PCT, Divisional, Continuation or C-1-P Application)

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name; I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**THERMOPLASTIC TRANSPARENT RESIN COMPOSITION AND METHOD OF
MANUFACTURING SAME**

This declaration is of the following type:

- ☐ original
- ☐ design
- ☒ national stage of PCT.
- ☐ divisional
- ☐ continuation
- ☐ continuation-in-part (C-I-P)

the specification of which: (complete (a), (b), or (c))

- (a) ☐ is attached hereto.
- (b) ☐ was filed on as Application Serial No. and was amended on (if applicable).
- (c) ☒ was described and claimed in PCT International Application No. PCT/KR 99/00101 filed on March 4, 1999 and was amended on (if applicable).

Acknowledgement of Review of Papers and Duty of Candor

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of the subject matter claimed in this application in accordance with Title 37, Code of Federal Regulations § 1.56.

In compliance with this duty there is attached an information disclosure statement. 37 CFR 1.98.

Priority Claim

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(a)-(d) of any foreign application(s) for patent or inventors certificate or of any PCT International Application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign applications) for patent or inventor's certificate or any PCT International Application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application on which priority is claimed

(complete (d) or (e))

- (d) ☐ no such applications have been filed.
- (e) ☒ such applications have been filed as follows:

PRIOR FOREIGN/PCT APPLICATION(S) FILED WITHIN 12 MONTHS (6 MONTHS FOR DESIGN) PRIOR TO SAID APPLICATION			
COUNTRY	APPLICATION NO.	DATE OF FILING (day, month, year)	DATE OF ISSUE (day, month, year)
Korea	1998-45699	29/10/1998	
ALL FOREIGN APPLICATION(S), IF ANY, FILED MORE THAN 12 MONTHS (6 MONTHS FOR DESIGN) PRIOR TO SAID APPLICATION			

Claim for Benefit of Prior U.S. Provisional Application(s)

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below:

Provisional Application Number	Filing Date

Claim for Benefit of Earlier U.S./PCT Application(s) under 35 U.S.C. 120 (complete this part only if this is a divisional, continuation or C-I-P application)

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior application(s) in the manner provided by the first paragraph of Title 35, United States Code § 112, 1 acknowledge the duty to disclose information as defined in Title 37, Code of Federal Regulations, § 1.56 which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application:

PCT/KR99/00101	March 4, 1999	pending
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)

Power of Attorney

As a named inventor, I hereby appoint Dana M. Raymond, Reg. No. 18,540; Frederick C. Carver, Reg. No. 17,021; Francis J. Hone, Reg. No. 18,662; Joseph D. Garon, Reg. No. 20,420; Arthur S. Tenser, Reg. No. 18,839; Ronald B. Hildreth, Reg. No. 19,498; Thomas R. Nesbitt, Jr., Reg. No. 22,075; Robert Neuner, Reg. No. 24,316; Richard G. Berkley, Reg. No. 25,465; Richard S. Clark, Reg. No. 26,154; Bradley B. Geist, Reg. No. 27,551; James J. Maune, Reg. No. 26,946; John D. Mumane, Reg. No. 29,836; Henry Tang, Reg. No. 29,705; Robert C. Scheinfeld, Reg. No. 31,300; John A. Fogarty, Jr., Reg. No. 22,348; Louis S. Sorell, Reg. No. 32,439 and Rochelle K. Seide Reg. No. 32,300 of the firm of BAKER & BOTTS, L.L.P., with offices at 30 Rockefeller Plaza, New York, New York 101 12, as attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

SEND CORRESPONDENCE TO: BAKER BOTTS, L.L.P. 30 ROCKEFELLER PLAZA, NEWYORK, N.Y. 10112 CUSTOMER NUMBER: 21003	DIRECT TELEPHONE CALLS TO: BAKER BOTTS, L.L.P. 212) 705-5000
---	--

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon

FULL NAME OF SOLE OR FIRST INVENTOR	LAST NAME <u>Yoo</u>	FIRST NAME <u>Keon-Hoon</u>	MIDDLE NAME	
RESIDENCE & CITIZENSHIP	CITY <u>Daejeon-city KRX</u>	STATE or FOREIGN COUNTRY Korea	COUNTRY OF CITIZENSHIP Korea	
POST OFFICE ADDRESS	POST OFFICE ADDRESS Hanbit Apt. 123-801, Eoeun-dong, Yuseong-gu	CITY Daejeon-city,	STATE or COUNTRY Korea	ZIP CODE
DATE June 5, 2000	SIGNATURE OF INVENTOR <u>K. H. Yoo</u>			

FULL NAME OF SOLE OR SECOND INVENTOR	LAST NAME <u>Shin</u>	FIRST NAME <u>Yang-Hyun</u>	MIDDLE NAME	
RESIDENCE & CITIZENSHIP	CITY <u>Yochon-city KRX</u>	STATE or FOREIGN COUNTRY Korea	COUNTRY OF CITIZENSHIP Korea	
POST OFFICE ADDRESS	POST OFFICE ADDRESS 29, Ansan-dong	CITY Yochon-city, Chollanam-do	STATE or COUNTRY Korea	ZIP CODE
DATE June 5, 2000	SIGNATURE OF INVENTOR <u>[Signature]</u>			

FULL NAME OF SOLE OR THIRD INVENTOR	LAST NAME <u>Lee</u>	FIRST NAME <u>Chan-Hong</u>	MIDDLE NAME	
RESIDENCE & CITIZENSHIP	CITY <u>Daejeon-city KRX</u>	STATE or FOREIGN COUNTRY Korea	COUNTRY OF CITIZENSHIP Korea	
POST OFFICE ADDRESS	POST OFFICE ADDRESS Ruckyhana Apt. 102-901, Shinseong-dong, Yuseong-gu	CITY Daejeon-city,	STATE or COUNTRY Korea	ZIP CODE
DATE June 5, 2000	SIGNATURE OF INVENTOR <u>Chan Hong Lee</u>			

Check proper box(es) for any added page(s) forming a part of this declaration

- ☐ Signature for ninth and subsequent joint inventors. Number of pages added _____
- ☐ Signature by administrator(trix), executor(trix) or legal representative for deceased or incapacitated inventor.
Number of pages added _____
- ☐ Signature for inventor who refuses to sign, or cannot be reached, by person authorized under 37 CFR 1.47.
Number of pages added _____